

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 8/04, 240/00	A1	(11) International Publication Number: WO 95/12623 (43) International Publication Date: 11 May 1995 (11.05.95)
(21) International Application Number: PCT/US94/12709 (22) International Filing Date: 3 November 1994 (03.11.94) (30) Priority Data: 08/148,137 3 November 1993 (03.11.93) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US). (72) Inventors: HENTGES, Steven, George; 4116 Emory, Houston, TX 77005 (US). JAGISCH, Frank, Carl; 3821 Lake LaRouge Drive, Baton Rouge, LA 70816 (US). SMITH, Edward, Francis; 8235 LaSalle Avenue, Baton Rouge, LA 70806 (US). (74) Agents: MULLER, William, G. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).		(81) Designated States: CN, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: AROMATIC TACKIFIER RESIN (57) Abstract <p>The invention comprises a hydrogenated hydrocarbon resin suitable as tackifier for acrylic adhesive polymers, having greater than 20 % aromatic protons after hydrogenation, a z-average molecular weight of less than about 1800, a narrow molecular weight distribution, typically of less than or equal to 2.1, and a softening point of from 40 °C to about 120 °C. It additionally comprises a method for preparing a hydrogenated aromatic tackifier resin suitable as tackifier for acrylic adhesive polymers comprising the steps of: a) polymerizing under Friedel-Crafts polymerization conditions steam-cracked petroleum distillates, or fractions thereof, having boiling points between about 135 °C and 220 °C and containing at least 40 % of by weight vinyl aromatic monomer contents, in the presence of a chain transfer agent; and b) catalytically hydrogenating the results of a) such that at least 75 % of the aromaticity is retained. The invention also comprises the use of this hydrogenated hydrocarbon resin as tackifier for an adhesive composition comprising one or more adhesive base polymers selected from acrylic copolymers, styrene block copolymers and ethylenevinyl ester copolymers wherein improved adhesive properties are observed.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

AROMATIC TACKIFIER RESIN

TECHNICAL FIELD

5 This invention relates to hydrogenated hydrocarbon resins, methods of preparation and uses as tackifiers for adhesive compositions comprising polar-group containing copolymers, particularly acrylic copolymers.

10 BACKGROUND OF THE INVENTION

 Acrylic polymer compositions have long been used as adhesive compositions, particularly in pressure-sensitive adhesive ("PSA") compositions. They exhibit adhesion to a broad variety of surfaces, show good low temperature performance, generally yield
15 attractively clear adhesives and possess excellent heat, age and UV stability. Acrylic adhesive polymers are available as organic(solvent) solutions, aqueous emulsions and as 100 percent solids, thermoplastic systems that are melt applied. Perhaps initially most important were the solvent acrylics, but the environmental/health/safety needs of industry have resulted in dramatic growth in water based acrylics.

20

 Traditionally acrylic PSA compositions have been tailored in characteristics by choice of acrylic monomers and polymerization conditions. This is unlike many other PSA compositions which traditionally have used tackifier resins, diluent oils, antioxidants, etc. to modify and enhance properties. With increasing desirability of water based
25 systems and often their demonstration of significant performance enhancements with tackifier resins, increasing adhesive performance demands and a desire to minimize the need to adjust and modify the acrylics polymerization process, tackifier resins suitable for acrylics are being sought. Both rosin derivatives, such as rosin esters, and hydrocarbon resins are commercially used as tackifiers in such blends. The rosin esters have been
30 preferred due to better compatibility with acrylics. However, the color and heat, age, and UV stability properties of rosin esters, even when hydrogenated, are inferior to those of acrylics and thus yield compositions of compromised properties when used as tackifiers for such systems. Hydrocarbon based resins have been employed as tackifiers for acrylics, but have often lacked the color, stability, compatibility or adhesive performance
35 that are sought in high performance acrylic adhesive systems, particularly those based on the more polar acrylic adhesive polymers. Newer hydrocarbon resins suitable as tackifiers for acrylic copolymer compositions are thus being sought, as are acrylic copolymer compositions having improved properties including tack, adhesion, and clarity.

- 2 -

U.S. patent 5,106,902 addresses internally tackified acrylic copolymer compositions prepared by dissolving a hydrogenated hydrocarbon resin in a liquid monomer mixture from which the copolymer is to be prepared by free radical initiated emulsion polymerization. A preferred resin is a hydrogenated petroleum resin prepared by Friedel-Crafts polymerization of steam-cracked petroleum distillates, or fractions thereof, having boiling points between about 135 °C and 220 °C and containing 10-100% by weight vinyl aromatic monomer contents. Preferably the aromatic content of the resin is about 20-65%, most preferably 30-50%. The resins typically are said to have ring and ball softening points of between about 10 °C. and about 100 °C.

EP-B-0 196 844 describes the use in aqueous acrylic polymers of an aqueous emulsion of a hydrocarbon resin having a softening point from 10 to 120 °C. and being a copolymer of predominantly C₅ olefins and diolefins and from 10 to 60 wt% of one or more monovinyl aromatic compounds. A preferred range of the monovinyl aromatic compounds is 10 to 40 wt%, more preferably 10 to 30 wt%. The resin is not said to be hydrogenated and is lacking in compatibility with acrylic polymers containing butyl acrylate.

EP-B-0 388 497 describes a hydrocarbon resin tackifier for butyl acrylate based polymers wherein the resin is derived from a petroleum cracked distillate comprising unsaturated materials which are C₅-C₆ mono-olefins and monovinyl aromatic monomers. These are used in proportions such that the resin has 35 to 85 wt% aromatic compound, preferably 40 to 70 wt%. The ring & ball softening point is 10 to 90 °C, preferably up to 80 °C. This resin as well is not said to be hydrogenated. In the examples no softening point above 75 °C is illustrated and % aromaticity is not greater than 80%.

SUMMARY OF INVENTION / INVENTION DISCLOSURE

The invention comprises a hydrogenated hydrocarbon resin suitable as a tackifier for acrylic adhesive polymers, having greater than 20% aromatic protons by NMR, a z-average molecular weight of less than about 1800, a narrow molecular weight distribution, typically of less than or equal to 2.1 polydispersity (M_w/M_n), and a softening point of from 40 °C to about 120 °C. It additionally comprises a method for preparing a hydrogenated aromatic tackifier resin suitable as a tackifier for acrylic adhesive polymers comprising the steps of: a) polymerizing under Friedel-Crafts polymerization conditions steam-cracked petroleum distillates, or fractions thereof, having boiling points between

- 3 -

about 135 °C and 220 °C and containing at least 40% by weight vinyl aromatic monomer contents, in the presence of 0-40% by weight of polymerization mixture of a chain transfer agent; and b) catalytically hydrogenating the results of a) such that at least 75% of the aromaticity is retained. The invention also comprises the use of this hydrogenated petroleum resin as a tackifier for an adhesive composition comprising one or more adhesive base polymers selected from acrylic copolymers, styrene block copolymers and ethylene-vinyl ester copolymers wherein improved adhesive properties are observed.

10

BEST MODE AND EXAMPLES OF THE INVENTION

15

20

25

30

35

The hydrogenated petroleum resin of the invention is typically one based upon catalytic polymerization of principally aromatic monomers which after polymerization and hydrogenation retains at least 20% aromatic protons by NMR, preferably at least 24% aromatic protons. It has a z-average molecular weight (M_z) less than about 1800, preferably less than 1300, more preferably less than 1100, and most preferably less than or equal to 1060. It has a polydispersity (M_w/M_n), or molecular weight distribution ("MWD"), of less than 2.1, preferably less than 1.90 and a ring and ball softening point (according to ASTM E-28) of 70 to 120 °C, preferably 80 to 100 °C, more preferably 90 to 100 °C. The invention resin also preferably exhibits an initial color after hydrogenation of greater than or equal to 10 Saybolt, preferably greater than or equal to 20 Saybolt, most preferably greater than or equal to 24 or 26 Saybolt. The resins meeting this description have been discovered to exhibit excellent compatibility with acrylic adhesive polymers, excellent color characteristics and stability and excellent tackification attributes.

Aromaticity of the invention resins is that measured by $^1\text{H-NMR}$, proton NMR, analysis in accordance with generally accepted procedures. The "retained aromaticity" is the ratio of the aromaticity by $^1\text{H-NMR}$ of the hydrogenated resin to that of the polymerized resin prior to hydrogenation. The molecular weight characterizations are determined by gel permeation chromatography utilizing a polystyrene calibration basis and then converting to a polyisobutylene calibration basis according to the equation $\log(\text{MW}_{\text{polyisobutylene}}) = 1.11 \times \log(\text{MW}_{\text{polystyrene}}) - 0.517$. Both procedures are described in relevant literature, see in particular WO-A-91 07472. The adhesive properties of adhesive compositions comprising the acrylic polymers and tackifier resins are typically measured in accordance with test methods set by the Pressure Sensitive Tape Council ("PSTC").

- 4 -

The terms acrylic polymers, acrylic adhesive polymers and acrylic copolymers are meant to include those polymers made from vinyl acids and/or esters which are polymerizable under free radical conditions, optionally with other ethylenically unsaturated monomers copolymerizable with them under the same free radical polymerization conditions. Preferably the vinyl acids and/or esters are selected from the (meth) acrylic acids or alkyl (meth) acrylates. Mixtures of one or more acids and/or esters are usually included.

These acrylate monomer mixtures generally comprise lower alkyl (meth) acrylates having 1 to 3 carbon atoms in the alkyl group of the ester and upper alkyl (meth) acrylates having 4 or more, usually up to about 14, preferably 4 to 8 carbon atoms. Other monomer components useful in accordance with the invention are the (meth) acrylic acid(s). Some preferred examples of monomers are as follows: acrylic acid, methacrylic acid, crotonic acid, maleic acid, itaconic acid, methyl (meth) acrylate, ethyl (meth) acrylate, propyl acrylate, 2-ethylhexyl acrylate, or n-butyl acrylate. Other monomeric material which can be employed can include acrylonitrile, vinyl acetate, vinylidene chloride, styrene, methyl styrene, and the like. The monomer mixture would contain from 1% to about 15%, preferably about 2% to about 6% of the (meth) acrylic acid; 0% to about 50%, preferably about 10% to 35%, lower alkyl (meth) acrylate; and from about 25% to 99%, preferably from 60% to about 88% higher alkyl (meth) acrylate. All percents are by weight of the monomer mixture.

The resins according to the invention typically can be prepared by catalytic polymerization of petroleum fractions identified as Heartcut Distillate or HCD and 0-40% by wt. of a chain transfer agent. Table IA illustrates a typical analysis of HCD, however it may vary considerably as to specific proportions of these typical components.

TABLE IA
TYPICAL HEARTCUT DISTILLATE (HCD) COMPOSITION (WT%)

Component (Wt%)	Typical Content	Typical Range
toluene	0.10	0 - 0.2
ethyl benzene	0.69	0.01 - 1.0
<i>m/p</i> - xylene	2.68	0.1 - 5.0
styrene	7.83	0.8 - 10.0
<i>o</i> - xylene	3.76	0.1 - 5.0
cumene	0.39	0.01 - 1.0
isopropyl cyclohexane	1.03	0.4 - 2.0
<i>n</i> - propyl benzene	2.18	0.8 - 3.0
3 - ethyl toluene	3.42	2.5 - 6.0
4 - ethyl toluene	1.71	1.0 - 2.5
tri methyl benzene	1.21	1.0 - 3.0
<i>alpha</i> - methyl styrene	3.39	2.5 - 6.0
<i>beta</i> - methyl styrene	0.74	0.5 - 2.0
<i>o/m</i> - methyl styrene	8.57	5.0 - 20.0
1,2,4 - tri methyl benzene	4.46	3.0 - 10.0
<i>o</i> - methyl styrene	2.31	1.0 - 6.0
tri methyl benzene	1.76	1.0 - 4.0
<i>beta</i> - methyl styrene	1.92	1.0 - 4.0
dicyclopentadiene / cymene	0.29	0.1 - 0.8
indane	1.31	0.5 - 2.5
indene	9.87	5.0 - 20.0
methyl indane	0.94	0.5 - 2.0
C ₄ benzenes	2.97	2.0 - 4.0
dimethyl styrene	2.81	2.0 - 4.0
divinyl Benzene	0.99	0.5 - 2.0
C ₂ styrenes	4.71	3.5 - 5.5
methyl indenenes	9.69	6.0 - 11.0
naphthalene	2.19	1.0 - 4.0
other non-reactives	6.08	1.0 - 10.0

- 6 -

More generally speaking the resins according to the invention can be prepared from vinyl aromatic streams comprising the following.

<u>Components</u>	<u>Typical Range</u>	<u>Table IA</u> <u>Typical HCD</u>
styrene	1-15	8
alkyl derivatives of styrene	15-40	25
indene	5-20	10
alkyl derivatives of indene	3-15	10
non-reactive components	15-76	47

5 Such streams can be derived from the steam-cracked petroleum distillates, or fractions thereof, having boiling points between 135 °C and 220 °C so long as they contain or are modified to contain sufficient vinyl aromatic contents. For example, an essentially pure styrene component can be added to commercially available petroleum distillate products that but for styrene otherwise fit this description. In this manner a
10 vinyl aromatic stream comprised of 11.4 wt.% styrene, 31.6 wt.% alkyl derivatives of styrene, 17.1 wt.% indene, 5 wt.% alkyl derivatives of indene, and the remainder non-reactive components (34.9 wt.%) was confirmed to be a suitable invention resin feedstock.

15 Polymerization is generally accomplished in accordance with the teachings of U.S. patent 4,078,132. According to this teaching, branched chain reactive aliphatic olefins are introduced during polymerization as chain transfer agents to achieve both lowered softening point and narrowed MWD. Though this document addresses preparation of substantially non-aromatic unsaturated thermoplastic resins, the teaching therein is
20 applicable to feed streams comprising HCD, or feed streams comprising vinyl aromatic monomer(s), to yield a highly aromatic precursor resin, which when hydrogenated can yield the aromatic tackifier resin of the invention. The feed streams should contain at least 40% by weight of total polymerizable monomers of vinyl aromatic monomers, preferably at least 50% by weight.

25

 The polymerization process of U.S. patent 4,078,132 is particularly suitable when practiced at polymerization temperatures of between -20° and 100 °C, preferably between 30° and 80 °C in the presence of a Friedel-Crafts catalyst, such as AlCl₃, and in the presence of the branched chain reactive olefin chain transfer agent, preferably isoamylenes
30 or dimate. Though most of the branched chain reactive olefin compounds of this prior art document will be effective if used in proper amounts, the isoamylenes are more reactive

- 7 -

and can be used advantageously in lesser amounts. The isoamylenes typically comprise isomers, for example, as shown in Table IB. These reactive chain transfer agents are preferably used in lesser amount than generally taught in this document, typically only 10-20, preferably 10-15 wt. % based upon total weight of this HCD or vinyl aromatic feedstream in order to control softening point and MWD. The process conditions of U.S. patent 4,514,554 also include description of polymerization of petroleum fraction feedstocks including isoamylenes. Both references are incorporated by reference for purposes of U.S. patent practice.

Hydrogenation can be generally accomplished in accordance with the teachings of U.S. patent 4,629,766, which is also incorporated by reference for purposes of U.S. patent practice. But other conventional means may alternatively be used. Typically temperatures of 200 to 300 °C are used, pressures of 10 to 300 kg/cm², and hydrogenating or hydrotreating catalysts such as Group VIII metals nickel, palladium, cobalt, ruthenium, platinum and rhodium, Group VI metals such as tungsten, chromium and molybdenum, and Group VII metals such as manganese and copper are used. These metals may be used singularly or in combination of two or more metals, in the metallic form, or in an activated form and may be used directly or on a solid support such as alumina or silica-alumina. A preferred catalyst is one comprising sulfided nickel-tungsten on a gamma-alumina support having a fresh catalyst surface area ranging from 120-300 m²/g and containing from 2-10% by weight nickel and from 10-25% by weight tungsten as described by U.S. patent 4,629,766. The hydrogenation is typically carried out with a hydrogen pressure of 20-300 atmospheres, preferably 150-250 atmospheres. Additional description of hydrogenation of aromatic resins appears in U.S. patent 3,926,878 and WO-A-91/07472, designated for the U.S. among other countries, both of which are incorporated by reference for purposes of U.S. patent practice.

Hydrogenation is performed at temperatures, pressures and times, and with effective catalysts, so as to retain at least 75% aromaticity, preferably at least 80%, more preferably at least 85%, and most preferably at least 90%. Optimization of the hydrogenation process can be empirically accomplished given the teachings presented in this application.

The aromatic tackifier resins of the invention can be used with water based acrylics when prepared as resin emulsions in accordance with any known means, such as exemplified in U.S. patent 4,414,346, U.S. patent 4,486,563 and U.S. patent 4,487,873. Typically the aromatic tackifier resin is emulsified in water and added to the water-based acrylic polymer to make a pressure sensitive adhesive composition. Alternatively, the

- 8 -

tackifier resin can be introduced into the acrylic polymerization mix for "internal tackification", for example, as described in U.S. patent 5,106,902, U.S. patent 5,013,784, U.S. patent 5,095,065 and U.S. patent 5,164,441. The disclosures of these patents are incorporated by reference for purposes of U.S. patent practice. The invention resins may
5 also be added directly to solvent acrylics or hot melt mixed with thermoplastic acrylics by conventional means.

Typical compositions comprise from 50 to 95 parts by weight acrylic polymer and 5 to 50 parts aromatic tackifier resin, or preferably 10-30 wt. % tackifier resin based upon
10 total of acrylic polymer and resin.

Conventional additive components are often also incorporated in acrylic polymer compositions and will also be suitable in accordance with this invention. Some examples are fillers such as clay, silica and calcium carbonate and plasticizers such as Paraplex®
15 WP-1, a plasticizer from Rohm and Haas Co. For the water based systems, defoamers, surfactants and thickeners are commonly used to aid in mixing and coating processes, and biocides are often employed for preservative properties. See additional description in Gehman, D. R., "Acrylic Adhesives", Handbook of Adhesives, 3rd. Ed., pp. 437-450 (Van Nostrand Reinhold, 1990).
20

Although primarily addressed to adhesive compositions, it will be apparent that the excellent adhesive qualities, color, age and UV stability, and compatibility of the resins in acrylic polymers will also provide advantages when such compositions are used as sealants, another area of significant use for acrylic polymers. Additionally, the resin of
25 the invention being high in aromatic content and low in color will be particularly suitable for use with ethylene-vinyl ester copolymers in hot-melt adhesive compositions, for example as described in U.S. patent 3,926,878, and with styrene block polymers, for example as described in WO-A-91 07472. Both references are incorporated by reference for purposes of U.S. patent practice.
30

The following examples are presented to illustrate the foregoing discussion. All parts, proportions and percentages are by weight unless otherwise indicated. Although the examples may be directed to certain embodiments of the present invention, they are not to be viewed as limiting the invention in any specific respect.

Example 1

The aromatic resins of this example were polymerized by a continuous, stirred reactor process using aluminum chloride as the catalyst in a nitrogen atmosphere at about 10 psig (0.7 kg/cm²). The aluminum chloride catalyst was added either directly to the reactor in powdered form or in an anhydrous paste form. This was formed by mixing the catalyst with a hydrogenated liquid resin at a weight ratio of 0.6 : 1. The relative proportions of catalyst and feedstreams are shown in Table II. These were individually pumped into the continuous stirred tank reactor over a period of 6 hours. Water was used as the co-catalyst and was present in the feedstreams at a level of 50-100 ppm. Thereafter, 200 grams of a 1:3 solution of isopropanol and water were added to the final 1200 g. reaction mixture to quench the catalyst. The polymerizate was water washed 2 to 3 additional times with the aqueous phase being separated after each wash.

The resin recovery step was carried out by heating to 250 °C, with a nitrogen sparge to remove raffinate followed by steam stripping to produce the precursor resin.

In this example, an isoamylene stream was used as chain transfer agent, except for Comparative Example D of Table II. The composition of the isoamylene stream for this example and other chain transfer streams are given below in Table IB.

- 10 -

TABLE IB
TYPICAL CHAIN TRANSFER AGENTS

Component (Wt%)	Dimate	Amylenes	Isoamylenes
1-pentene	0.01	20.5	-
2-methyl-1-butene	0.03	30.3	6.55
isoprene	-	0.77	-
<i>trans</i> -2-pentene	0.03	17.1	-
<i>cis</i> -2-pentene	0.01	8.45	-
2-methyl-2-butene	0.13	5.36	93.3
<i>trans</i> -1,3-pentadiene	0.02	-	-
<i>cis</i> -1,3-pentadiene	0.01	-	-
cyclopentene	0.02	-	-
4-methyl-1-pentene	0.64	-	0.04
2,3-dimethyl-1-butene	1.48	-	-
<i>trans</i> -4-methyl-2-pentene	13.4	-	-
2-methyl-1-pentene	4.10	-	-
1-hexene	0.26	-	-
<i>trans</i> -3-hexene	4.02	-	-
<i>cis</i> & <i>trans</i> -2-hexene and <i>cis</i> -3-hexene	10.2	-	-
2-methyl-2-pentene	31.3	-	-
2,3-dimethyl-2-butene	2.96	-	-
<i>cis</i> -2-hexene	4.27	-	-
benzene	0.04	-	-
dicyclopentadiene	-	0.59	-

5 The following Table II gives the reaction conditions and properties of the precursor resins polymerized by the process described above.

- 11 -

TABLE II

Resin Example	A	B	C	D	E
Feed Composition, wt. %					
Chain Transfer Agent	14 ¹	10 ¹	10 ¹	0	25 ²
Heartcut Distillate ³	86	90	90	100	75
Polymerization					
AlCl ₃ Catalyst, wt. %	0.6	0.6	0.6	0.6	0.6
Reactor Temperature, °C	40	40	40	40	40
Reactor Pressure, psig (kg/cm ²)	10 (0.7)	10 (0.7)	10 (0.7)	10 (0.7)	10 (0.7)
Resin Properties					
Softening Point, °C	92	95	98	112	88
¹ H-NMR, % aromatic protons	27	nm	29	30	26
Gardner Color	nm	nm	nm	10	nm
GPC Molecular Weight					
M _w	450	570	525	860	600
M _n	280	290	310	440	330
M _w /M _n	1.6	1.8	1.7	2.0	1.8
M _z	760	1010	965	1700	1430

notes : 1) Isoamylene; 2) Dimate; 3) HCD is that of Typical Content in Table IA; 4) "nm" is not measured

5

The aromatic resins A-E were each blended with 60 wt% of an aliphatic solvent (Varsol®, Exxon Chemical Co., USA) and then hydrogenated in accordance with the examples and teachings of U.S. patent 4,629,766, at a hydrogen pressure of 3800 psig (267 kg/cm²) for 1.5 hours residence time with an exotherm maximum temperature of 240 °C over the preferred sulfided nickel-tungsten catalyst described above. This resin was then recovered by heating to 250 °C with a nitrogen sparge and stream stripping to produce the finished resin.

The thus hydrogenated resins A-E exhibited the characteristics in Table III. Aged Gardner Color, was as measured after 5 hrs. at a temperature of 175 °C.

15

TABLE III

Resin Example	A	B	C	D	E
Softening Point, °C	92	95	98	119	87
¹ H-NMR, % aromatic protons	24	29	27	29	21
Retained Aromaticity %	89		93	97	81
Saybolt color	29	27	28	20	24
Aged Gardner Color	nm	4.0	4.7	17	nm
GPC Molecular Weight					
M_w	445	520	540	860	530
M_n	300	300	330	440	330
M_w/M_n	1.5	1.7	1.6	2.0	1.6
M_z	700	920	916	1700	970

5 Example 2

This example illustrates the enhancements available from use of a resin in accordance with the invention when compared against a hydrogenated rosin ester (Foral® 85 emulsion, Hercules, Inc., U.S.A.) commercially used to tackify acrylic adhesive polymers, particularly the more polar acrylic polymers such as those based on butyl acrylate. This invention resin prepared as in Example 1, after hydrogenation exhibited 25% aromatic protons, an M_z of 940, MWD of 1.7, and a ring and ball softening point (according to ASTM E-28) of 96°C. The invention resin also exhibited a color of 14 Saybolt. This resin was then emulsified in accordance with the teachings of U.S. patent 4,414,346, U.S. patent 4,486,563, and U.S. patent 4,487,873. In this case the resinplast used to facilitate emulsification was heptane.

Robond® PS-83D, Rhoplex® N-619 and Rhoplex® N-580 are water-based acrylic emulsions available from Rohm & Haas Co. Ucar® 174 is a water-based acrylic emulsion from Union Carbide. These commercial acrylic emulsions are believed to be based on butyl acrylate. Table IV illustrates PSA performance using standard test methods. Each adhesive composition was blended in aqueous form in parts by weight (solids or dry basis) and coated onto mylar film to 1.25 mils dry-film thickness. The coated films were dried for 2 min. at 100°C. The films were then covered with release paper and allowed to set overnight at room temperature and 50% humidity.

- 13 -

Both the hydrogenated rosin ester and the invention resin show good compatibility with these acrylic polymers as evidenced by the existence of excellent film clarity. Both resins enhance adhesive aggressiveness and specific adhesion as would be expected of a properly selected resin composition. However, the invention resin results in much less adhesive softening/loss in shear strength ("hold to stainless steel"/creep under load) than the rosin ester. This is a significant drawback associated with rosin esters. The invention resin also shows enhanced wetting/adhesion to kraft paper (corrugated board) as demonstrated by fiber tear values. Finally, these attributes are combined with the invention resin's superior initial color (water white versus 3 Gardner for the rosin ester) and color, age and UV stability. Color and stability now more closely match the inherent qualities of acrylic polymers.

TABLE IV

Formulations	1	2	3	4	5	6	7	8	9	10	11	12
Robond PS-83D	100				75				75			
Rhoplex N-619		100				75				75		
Rhoplex N-580			100				75				75	
Ucar 174				100				75				75
Invention Resin					25	25	25	25				
Foral 85									25	25	25	25
PSA Performance (1)												
Loop Tack to SS, ppi (g/cm)	1.6 (282)	3.6 (635)	1.2 (212)	3.1 (547)	3.0 (530)	3.1 (547)	2.1 (371)	3.5 (618)	2.6 (459)	4.0 (706)	1.7 (300)	4.0 (706)
Loop Tack to Kraft Paper, ppi (g/cm)	1.9 (335)	2.6 (459)	1.4 (247)	2.2 (388)	1.8 (318)	1.5 (265)	1.8 (318)	1.8 (318)	2.0 (353)	2.3 (406)	1.5 (265)	2.0 (353)
% Fiber Tear (visual)	2	18	0	1	67	100	25	67	0	17	5	0
180° Peel Strength to SS, ppi (g/cm)	2.2 (388)	3.3 (582)	1.5 (265)	3.5 (618)	3.1 (547)	4.1 (724)	2.5 (441)	3.8 (671)	3.4 (600)	6.0 (1059)	2.3 (406)	4.6 (812)
180° Peel Strength to PE, ppi (g/cm)	0.5 (88)	1.3 (229)	0.3 (53)	0.9 (158)	1.3 (229)	0.6 (106)	1.1 (194)	1.7 (300)	1.6 (282)	2.3 (406)	1.2 (212)	2.0 (353)
178° Hold to SS, hrs (0.5" X 0.5" X 500g)	11.3	5.8	1.8	4.6	5.8	9.3	11.7	4.3	2.8	3.2	13.0	2.8
Film Clarity (visual)	clear	clear	clear	clear	clear	clear	clear	clear	clear	clear	clear	clear

(1) Test methods: loop tack - one inch wide adhesive strip contacted 3-4" along its length to stainless steel panel and then immediately debonded at a 2 inches/min jaw separation speed; peel strength - PSTC 1; hold to stainless steel (SS) - PSTC 7.

- 15 -

Example 3

The performance characteristics of a hydrogenated resin in accordance with the invention were also compared against commercially available resins sold as high aromaticity hydrogenated resins. This invention resin exhibited 24 % aromatic protons, an M_z of 1050, MWD of 1.6, and a ring and ball softening point (according to ASTM E-28) of 95 °C. The invention resin also exhibited a color of 26 Saybolt.

Arkon® M-90 and Arkon® P-90 (Arakawa Chemical, Japan) are 90 °C softening point resins indicated by their manufacturer to be aromatic resins hydrogenated to different degrees. Likewise, Arkon® M-100 and Arkon® P-100 are 100°C softening point, aromatic resins with differing degrees of hydrogenation. Analysis by $^1\text{H-NMR}$ shows that the invention resin possesses considerably more aromaticity than the Arkon M series at 7.3 % and the Arkon P series at 1.2% aromatic protons. This differentiation yielded much superior performance as an acrylic polymer tackifier.

In order to compare resins at equal softening point the Arkon® M-90 and M100 were blended 50/50 to achieve a 95°C softening point. In the same manner Arkon® P-90 and Arkon® P-100 were also blended. These blended compositions were emulsified in the manner described earlier. Adhesive performance comparison with the invention resin is shown in Table V. Adhesive film preparation and test methods are the same as in Example 2. The invention resin clearly exhibits better tack and adhesion than the commercial hydrogenated aromatic resins (these resins actually reduce the properties of the adhesive base polymers). The invention resin also produces films with greater clarity.

TABLE V

Formulations	1	2	3	4	5	6	7	8	9	10	11	12
Invention Resin	25	25	25	25								
Arkron M-90/100					25	25	25	25				
Arkron P-90/100									25	25	25	25
Robond PS-83D	75				75				75			
Rhoplex N-619		75				75				75		
Rhoplex N-580			75				75				75	
Ucar 174				75				75				75
PSA Performance (1)												
Loop Tack to Kraft Paper, ppi (g/cm)	1.5 (265)	1.4 (247)	1.6 (282)	1.6 (282)	0.2 (35)	0.5 (88)	0.2 (35)	1.1 (194)	0.1 (18)	0 (0)	0 (0)	0.9 (158)
% Fiber Tear (visual)	40	100	50	90	0	0	0	5	0	0	0	0
180° Peel Strength to SS, ppi (g/cm)	2.3 (406)	3.4 (600)	2.6 (459)	3.4 (600)	1.0 (177)	1.3 (229)	0.7 (124)	1.2 (212)	0.8 (141)	0.6 (106)	0.5 (88)	1.1 (194)
180° Peel Strength to PE, ppi (g/cm)	1.1 (194)	0.8 (141)	1.0 (177)	1.5 (265)	0.6 (106)	0.3 (53)	0.4 (71)	0.7 (124)	0.3 (53)	0.2 (35)	0.2 (35)	0.4 (71)

(1) Test methods: loop tack - one inch wide adhesive strip contacted 3-4" along its length to stainless steel panel and then immediately debonded at a 2 inches/min jaw separation speed; peel strength - PSTC 1; hold to stainless steel (SS) - PSTC 7.

- 17 -

CLAIMS:

1. A hydrogenated hydrocarbon resin having greater than 20% aromatic protons by NMR, a z-average molecular weight by GPC of less than 1800, a molecular weight distribution (M_w/M_n) of less than 2.1, and a ring & ball softening point of from 40° C. to about 120° C.
2. The resin according to Claim 1 wherein said z average molecular weight is less than 1100 and said softening point is greater than 90° and less than or equal to 100° C.
3. The resin according to Claim 1 having greater than 24% aromatic protons after hydrogenation.
4. The resin according to Claim 1 wherein the MWD is less than 1.7.
5. The resin according to Claim 1 having initial Saybolt color greater than or equal to 20.
6. A method for preparing a hydrogenated aromatic tackifier resin suitable as a tackifier for acrylic adhesive polymers comprising the steps of :
 - a) polymerizing under Friedel-Crafts polymerization conditions steam-cracked petroleum distillates, or fractions thereof, having boiling points between about 135 ° C. and 220 ° C. and containing at least 40% by weight vinyl aromatic monomer contents, in the presence of 0-40% by weight of polymerization mixture of a chain transfer agent; and
 - b) catalytically hydrogenating the results of a) such that at least 75% of the aromaticity is retained.
7. The method according to Claim 6 wherein an isoamylene chain transfer agent is used in an amount of 10-20% by weight of polymerization mixture.
8. The method according to Claim 6 wherein step b) is done using a sulfided nickel-tungsten on a gamma-alumina support.
9. A use of the hydrogenated hydrocarbon resin according to claim 1 as a tackifier for an adhesive composition comprising one or more acrylic copolymers.

- 18 -

10. A use of the hydrogenated hydrocarbon resin according to claim 1 as a tackifier for a sealant composition comprising one or more acrylic copolymers.

5 11. The use according to Claim 9 additionally comprising one or more additives selected from fillers, plasticizers, defoamers, surfactants, thickeners and biocides.

10 12. The use according to Claim 10 additionally comprising one or more additives selected from fillers, plasticizers, defoamers, surfactants, thickeners and biocides.

15 13. A composition of matter comprising a) one or more acrylic copolymers, and b) a hydrogenated petroleum resin having greater than 20% aromatic protons after hydrogenation, a z-average molecular weight by GPC of less than 1800, a molecular weight distribution (M_w/M_n) of less than 2.1, and a ring & ball softening point of from 40 °C. to about 120 °C.

14. The composition according to Claim 13 used as an adhesive composition.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/12709

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F8/04 C08F240/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO,A,91 13106 (EXXON CHEMICAL PATENTS INC.) 5 September 1991 see page 5, line 10 - page 7, line 18 see page 8, line 1 - line 16 see page 10, line 4 - line 20; claims 1-6; examples 2,4 ---	1-6,8-14
X	US,A,4 952 639 (KATSUMI MINOMIYA) 28 August 1990 see the whole document ---	1-6
A	WO,A,93 19097 (EXXON CHEMICAL PATENTS INC.) 30 September 1993 see claims 1-9 --- -/-	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

20 February 1995

Date of mailing of the international search report

- 8. 03. 95

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Permentier, W

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/12709

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 234 856 (EXXON CHEMICAL PATENTS INC.) 2 September 1987 see page 6, line 11 - page 7, line 31; claims 1-23 ---	1,6,7
A	WO,A,90 15111 (EXXON CHEMICAL PATENTS INC.) 13 December 1990 cited in the application see page 4, line 17 - page 5, line 23 see page 6, line 6 - line 14; claims 1-28 ---	1
A	EP,A,0 196 844 (EXXON CHEMICAL PATENTS INC.) 8 October 1986 cited in the application see claims 1-10 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/12709

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9113106	05-09-91	US-A- 5171793	15-12-92
		AU-B- 643163	04-11-93
		AU-A- 7310091	18-09-91
		EP-A- 0516733	09-12-92
		JP-T- 5504592	15-07-93
US-A-4952639	28-08-90	JP-A- 1033105	03-02-89
		JP-B- 6025214	06-04-94
WO-A-9319097	30-09-93	EP-A- 0631588	04-01-95
EP-A-0234856	02-09-87	US-A- 4677176	30-06-87
		US-A- 4683268	28-07-87
		CA-A- 1298026	24-03-92
		DE-A- 3774726	09-01-92
		JP-T- 3502703	20-06-91
		US-A- 4933409	12-06-90
		WO-A- 8705033	27-08-87
		US-A- 4810574	07-03-89
		US-A- 4853432	01-08-89
WO-A-9015111	13-12-90	US-A- 5095065	10-03-92
		US-A- 5164441	17-11-92
		US-A- 5317055	31-05-94
EP-A-0196844	08-10-86	AU-B- 583363	27-04-89
		AU-A- 5507686	02-10-86
		CA-A- 1278132	18-12-90
		DE-A- 3686734	22-10-92
		JP-A- 61275363	05-12-86
		US-A- 5284891	08-02-94

BLANK PAGE